



ORE RESEARCH & EXPLORATION P/L ABN 28 006 859 856
37A Hosie Street · Bayswater North · VIC 3153 · AUSTRALIA
☎ 61 3 9729 0333 ☎ 61 3 9729 8338
📧 info@ore.com.au 🌐 www.ore.com.au

CERTIFICATE OF ANALYSIS FOR

**LATERITIC SCANDIUM (NICKEL-COBALT) ORE
CERTIFIED REFERENCE MATERIAL
OREAS 198**



Table 1. Certified Values, SDs, 95% Confidence and Tolerance Limits for OREAS 198.

Constituent	Certified Value	1SD	95% Confidence Limits		95% Tolerance Limits	
			Low	High	Low	High
Borate Fusion XRF						
Al ₂ O ₃ , Aluminium(III) oxide (wt.%)	15.81	0.117	15.75	15.88	15.73	15.89
CaO, Calcium oxide (wt.%)	0.346	0.006	0.343	0.348	0.337	0.354
Co, Cobalt (ppm)	804	17	794	814	790	819
Cr ₂ O ₃ , Chromium(III) oxide (wt.%)	0.285	0.005	0.283	0.288	0.282	0.289
Cu, Copper (ppm)	491	32	470	512	472	510
Fe ₂ O ₃ , Iron(III) oxide (wt.%)	45.99	0.230	45.88	46.10	45.77	46.20
K ₂ O, Potassium oxide (wt.%)	0.101	0.007	0.097	0.105	0.098	0.105
MgO, Magnesium oxide (wt.%)	0.798	0.031	0.779	0.817	0.783	0.813
MnO, Manganese oxide (wt.%)	1.53	0.021	1.52	1.54	1.52	1.54
Na ₂ O, Sodium oxide (wt.%)	0.144	0.010	0.139	0.149	0.131	0.157
Ni, Nickel (ppm)	688	70	645	730	660	716
P ₂ O ₅ , Phosphorus(V) oxide (wt.%)	0.161	0.005	0.158	0.164	0.158	0.163
Sc, Scandium (ppm)	414	17	396	431	403	425
SiO ₂ , Silicon dioxide (wt.%)	22.79	0.126	22.73	22.85	22.64	22.94
TiO ₂ , Titanium dioxide (wt.%)	1.36	0.020	1.35	1.37	1.35	1.37
Zn, Zinc (ppm)	207	12	198	216	199	215
Thermogravimetry						
LOI ¹⁰⁰⁰ , Loss On Ignition @1000°C (wt.%)	10.18	0.218	10.06	10.31	10.12	10.24
Borate / Peroxide Fusion ICP						
Al ₂ O ₃ , Aluminium(III) oxide (wt.%)	15.56	0.358	15.34	15.79	15.31	15.81
As, Arsenic (ppm)	< 30	IND	IND	IND	IND	IND
Ba, Barium (ppm)	284	10	278	289	274	293
Be, Beryllium (ppm)	1.43	0.34	1.29	1.56	IND	IND
CaO, Calcium oxide (wt.%)	0.342	0.048	0.317	0.367	0.324	0.361
Ce, Cerium (ppm)	75	4.3	70	79	72	77
Co, Cobalt (ppm)	807	19	797	816	787	826
Cr ₂ O ₃ , Chromium(III) oxide (wt.%)	0.281	0.008	0.277	0.285	0.272	0.290
Cs, Cesium (ppm)	0.86	0.082	0.82	0.89	0.80	0.91
Cu, Copper (ppm)	495	22	479	511	478	513
Dy, Dysprosium (ppm)	4.19	0.227	4.04	4.35	3.64	4.74
Er, Erbium (ppm)	2.26	0.164	2.21	2.31	2.07	2.45
Eu, Europium (ppm)	1.45	0.097	1.38	1.51	IND	IND
Fe ₂ O ₃ , Iron(III) oxide (wt.%)	45.22	1.121	44.64	45.80	44.67	45.77
Ga, Gallium (ppm)	22.2	1.85	20.6	23.8	20.9	23.5
Gd, Gadolinium (ppm)	4.83	0.352	4.45	5.22	4.46	5.20
Hf, Hafnium (ppm)	2.54	0.143	2.40	2.68	IND	IND
Ho, Holmium (ppm)	0.82	0.051	0.79	0.85	IND	IND
K ₂ O, Potassium oxide (wt.%)	0.107	0.023	0.090	0.124	0.085	0.128
La, Lanthanum (ppm)	10.1	0.80	9.4	10.8	9.5	10.7
Li, Lithium (ppm)	22.2	1.18	21.3	23.2	20.9	23.6
Lu, Lutetium (ppm)	0.33	0.04	0.30	0.37	IND	IND

Note: intervals may appear asymmetric due to rounding

Table 1 continued.

Constituent	Certified Value	1SD	95% Confidence Limits		95% Tolerance Limits	
			Low	High	Low	High
Borate / Peroxide Fusion ICP continued						
MgO, Magnesium oxide (wt.%)	0.773	0.029	0.757	0.789	0.748	0.798
MnO, Manganese oxide (wt.%)	1.49	0.041	1.47	1.51	1.46	1.52
Mo, Molybdenum (ppm)	< 5	IND	IND	IND	IND	IND
Na ₂ O, Sodium oxide (wt.%)	0.149	0.019	0.124	0.173	IND	IND
Nb, Niobium (ppm)	4.79	0.293	4.58	5.00	4.49	5.10
Nd, Neodymium (ppm)	16.6	0.81	16.0	17.2	15.5	17.7
Ni, Nickel (ppm)	688	28	676	700	666	710
P ₂ O ₅ , Phosphorus(V) oxide (wt.%)	0.150	0.020	0.138	0.162	IND	IND
Pb, Lead (ppm)	< 20	IND	IND	IND	IND	IND
Pr, Praseodymium (ppm)	3.58	0.180	3.45	3.72	3.43	3.74
Rb, Rubidium (ppm)	8.15	0.535	7.92	8.38	7.76	8.55
Sc, Scandium (ppm)	401	19	392	411	391	412
SiO ₂ , Silicon dioxide (wt.%)	22.52	0.429	22.37	22.66	22.02	23.01
Sm, Samarium (ppm)	5.18	0.344	5.01	5.34	4.85	5.50
Sn, Tin (ppm)	2.58	1.22	1.15	4.01	IND	IND
Sr, Strontium (ppm)	68	4.8	65	71	65	70
Ta, Tantalum (ppm)	0.38	0.04	0.34	0.41	IND	IND
Tb, Terbium (ppm)	0.75	0.056	0.71	0.79	IND	IND
Th, Thorium (ppm)	3.30	0.181	3.19	3.40	2.98	3.61
TiO ₂ , Titanium dioxide (wt.%)	1.34	0.049	1.31	1.37	1.31	1.37
Tm, Thulium (ppm)	0.34	0.04	0.33	0.35	IND	IND
U, Uranium (ppm)	1.32	0.107	1.28	1.35	IND	IND
V, Vanadium (ppm)	644	33	623	665	622	666
W, Tungsten (ppm)	1.12	0.18	0.90	1.34	IND	IND
Y, Yttrium (ppm)	16.8	1.8	15.8	17.8	15.7	17.9
Yb, Ytterbium (ppm)	2.21	0.124	2.13	2.30	1.96	2.47
Zn, Zinc (ppm)	212	13	206	219	200	225
Zr, Zirconium (ppm)	80	5.5	75	85	72	88
Infrared Combustion						
C, Carbon (wt.%)	0.246	0.016	0.235	0.257	0.232	0.259
Gas / Liquid Pycnometry						
SG, Specific Gravity (Unity)	3.21	0.102	3.11	3.31	3.15	3.27

Note: intervals may appear asymmetric due to rounding

INTRODUCTION

OREAS reference materials are intended to provide a low cost method of evaluating and improving the quality of analysis of geological samples. To the geologist they provide a means of implementing quality control in analytical data sets generated in exploration from the grass roots level through to prospect evaluation, and in grade control at mining operations. To the analyst they provide an effective means of calibrating analytical equipment, assessing new techniques and routinely monitoring in-house procedures.

SOURCE MATERIALS

OREAS 198 has been prepared from a blend of scandium mineralised laterite sourced from the Nyngan (Gilgai and Honeybugle) deposits, located about 450kms northwest of Sydney (Australia), supplemented with ferruginous soil (sourced from soils developed over Tertiary tholeiitic basalt in eastern Melbourne, Australia).

The Nyngan scandium ore is sourced from the upper lateritic zone consisting haematitic and limonitic clays from humid weathering of mafic/ultramafic rocks that intruded Cambrian-Ordovician metasediments.

COMMINUTION AND HOMOGENISATION PROCEDURES

The material constituting OREAS 198 was prepared in the following manner:

- drying to constant mass at 105°C;
- crushing and milling of the barren ferruginous soil to >95% minus 75 microns;
- crushing and milling of the ore material to 100% minus 35 microns;
- preliminary homogenisation and check assaying of ore source material;
- final homogenisation by blending the source materials in specific ratios to achieve target grades;
- packaging in 10g units sealed in laminated foil pouches and 1kg units in plastic jars.

ANALYTICAL PROGRAM

Seventeen commercial analytical laboratories participated in the program to certify the analytes reported in Table 1. The following methods were employed:

- Borate fusion with XRF for common nickel laterite assemblage (up to 14 laboratories depending on the analyte);
- Thermogravimetric analysis of LOI at 1000°C (15 labs);
- Borate or peroxide fusion for full elemental suite ICP-OES and ICP-MS finishes (up to 15 laboratories depending on the element);
- C and S by IR combustion furnace (14 labs);
- Specific gravity by gas (6 labs) or liquid (3 labs) pycnometry.

For the round robin program ten 250g test units were taken at predetermined intervals during the bagging stage, immediately following homogenisation and are considered representative of the entire 130kg batch. The six samples received by each laboratory were obtained by taking one 20g scoop split from each of six different test units. This format maximised representivity of the parent batch at each lab. Table 1 presents the 69 certified values together with their associated 1SD's, 95% confidence and tolerance limits and Table 2 below shows 20 indicative values. Table 3 provides performance gate intervals for the certified values based on their associated pooled standard deviations. Tabulated results of all elements together with analytical method codes, uncorrected means, medians, standard deviations, relative standard deviations and per cent deviation of lab means from the corrected mean of means (PDM³) are presented in the detailed certification data for this CRM (**OREAS 198 DataPack.xlsx**).

Table 2. Indicative Values for OREAS 198.

Constituent	Unit	Value	Constituent	Unit	Value	Constituent	Unit	Value
Borate Fusion XRF								
As	ppm	15.1	Pb	ppm	< 50	Zr	ppm	93
BaO	ppm	488	SO ₃	wt.%	0.055			
Cl	ppm	544	V ₂ O ₅	ppm	1060			
Borate / Peroxide Fusion ICP								
Ag	ppm	< 5	Ge	ppm	3.08	Sb	ppm	1.14
B	ppm	< 50	In	ppm	0.16	Se	ppm	< 20
Bi	ppm	0.16	Re	ppm	< 0.1	Te	ppm	< 1
Cd	ppm	< 10	S	wt.%	0.028	Tl	ppm	0.38
Infrared Combustion								
S	wt.%	0.024						

Note: the number of significant figures reported is not a reflection of the level of certainty of stated values. They are instead an artefact of ORE's in-house CRM-specific LIMS.

STATISTICAL ANALYSIS

Certified Values, Confidence Limits, Standard Deviations and Tolerance Limits

(Table 1) have been determined for each analyte following removal of individual, laboratory dataset (batch) and 3SD outliers (single iteration). For individual outliers within a laboratory batch the z-score test is used in combination with a second method that determines the per cent deviation of the individual value from the batch median. Outliers in general are selected on the basis of z-scores > 2.5 and with per cent deviations (i) > 3 and (ii) more than three times the average absolute per cent deviation for the batch. In certain instances statistician's prerogative has been employed in discriminating outliers. Each laboratory data set mean is tested for outlying status based on z-score discrimination and rejected if > 2.5. After individual and laboratory data set (batch) outliers have been eliminated a non-iterative 3 standard deviation filter is applied, with those values lying outside this window also relegated to outlying status. The Certified Values are the means of accepted laboratory means after outlier filtering.

The 95% Confidence Limits are inversely proportional to the number of participating laboratories and inter-laboratory agreement. It is a measure of the reliability of the certified value. A 95% confidence interval indicates a 95% probability that the true value of the analyte under consideration lies between the upper and lower limits. *95% Confidence Limits should not be used as control limits for laboratory performance.*

Standard Deviation values (1SDs) are reported in Table 1 and provide an indication of a level of performance that might reasonably be expected from a laboratory being monitored by this CRM in a QA/QC program. The SD's take into account errors attributable to measurement uncertainty and CRM variability. For an effective CRM the contribution of the latter should be negligible in comparison to measurement errors. The SD values thus include all sources of measurement uncertainty: between-lab variance, within-run variance (precision errors) and CRM variability. OREAS prepared reference materials have a level of homogeneity such that the observed variance from repeated analysis has its origin almost exclusively in the analytical process rather than the reference material itself.

The SD for each analyte's certified value is calculated from the same filtered data set used to determine the certified value, i.e. after removal of any individual, lab dataset (batch) and 3SD outliers (single iteration). These outliers can only be removed after the absolute homogeneity of the CRM has been independently established, i.e. the outliers must be confidently deemed to be analytical rather than arising from inhomogeneity of the CRM. **The standard deviation is then calculated for each analyte from the pooled accepted analyses generated from the certification program.**

In the application of SD's in monitoring performance it is important to note that not all laboratories function at the same level of proficiency and that different methods in use at a particular laboratory have differing levels of precision. Each laboratory has its own inherent SD (for a specific concentration level and analyte-method pair) based on the analytical process and this SD is not directly related to the round robin program.

The majority of data generated in the round robin program was produced by a selection of world class laboratories. The SD's thus generated are more constrained than those that would be produced across a randomly selected group of laboratories. To produce more generally achievable SD's the 'pooled' SD's provided in this report include inter-lab bias. This 'one size fits all' approach may require revision at the discretion of the QC manager concerned following careful scrutiny of QC control charts.

Table 3 shows **Performance Gates** calculated for two and three standard deviations. As a guide these intervals may be regarded as warning or rejection for multiple 2SD outliers, or rejection for individual 3SD outliers in QC monitoring, although their precise application should be at the discretion of the QC manager concerned. A second method utilises a 5% window calculated directly from the certified value. Standard deviation is also shown in relative percent for one, two and three relative standard deviations (1RSD, 2RSD and 3RSD) to facilitate an appreciation of the magnitude of these numbers and a comparison with the 5% window. Caution should be exercised when concentration levels approach lower limits of detection of the analytical methods employed as performance gates calculated from standard deviations tend to be excessively wide whereas those determined by the 5% method are too narrow.

Tolerance Limits (ISO Guide 3207) were determined using an analysis of precision errors method and are considered a conservative estimate of true homogeneity. The meaning of tolerance limits may be illustrated for scandium (Sc) by fusion ICP, where 99% of the time ($1-\alpha=0.99$) at least 95% of subsamples ($\rho=0.95$) will have concentrations lying between 391 and 412 ppm. Put more precisely, this means that if the same number of subsamples were taken and analysed in the same manner repeatedly, 99% of the tolerance intervals so constructed would cover at least 95% of the total population, and 1% of the tolerance intervals would cover less than 95% of the total population (ISO Guide 35). *Please note that tolerance limits pertain to the homogeneity of the CRM only and should not be used as control limits for laboratory performance.*

Based on the statistical analysis of the results of the inter-laboratory certification program it can be concluded that OREAS 198 is fit-for-purpose as a certified reference material (see 'Intended Use' below).

Table 3. Performance Gates for OREAS 198.

Constituent	Certified Value	Absolute Standard Deviations					Relative Standard Deviations			5% window	
		1SD	2SD Low	2SD High	3SD Low	3SD High	1RSD	2RSD	3RSD	Low	High
Borate Fusion XRF											
Al ₂ O ₃ , wt. %	15.81	0.117	15.58	16.05	15.46	16.17	0.74%	1.48%	2.22%	15.02	16.60
CaO, wt. %	0.346	0.006	0.334	0.358	0.327	0.364	1.77%	3.55%	5.32%	0.329	0.363
Co, ppm	804	17	770	839	753	856	2.14%	4.28%	6.42%	764	845
Cr ₂ O ₃ , wt. %	0.285	0.005	0.275	0.296	0.269	0.301	1.86%	3.73%	5.59%	0.271	0.300
Cu, ppm	491	32	427	555	395	586	6.49%	12.97%	19.46%	466	515
Fe ₂ O ₃ , wt. %	45.99	0.230	45.53	46.45	45.30	46.68	0.50%	1.00%	1.50%	43.69	48.29
K ₂ O, wt. %	0.101	0.007	0.087	0.115	0.080	0.122	6.97%	13.95%	20.92%	0.096	0.106
MgO, wt. %	0.798	0.031	0.736	0.861	0.704	0.892	3.92%	7.84%	11.76%	0.758	0.838
MnO, wt. %	1.53	0.021	1.49	1.57	1.47	1.59	1.38%	2.77%	4.15%	1.45	1.61
Na ₂ O, wt. %	0.144	0.010	0.125	0.163	0.115	0.173	6.63%	13.27%	19.90%	0.137	0.151
Ni, ppm	688	70	548	828	477	898	10.18%	20.37%	30.55%	653	722
P ₂ O ₅ , wt. %	0.161	0.005	0.150	0.171	0.145	0.177	3.34%	6.68%	10.01%	0.153	0.169
Sc, ppm	414	17	379	449	361	466	4.22%	8.44%	12.66%	393	435
SiO ₂ , wt. %	22.79	0.126	22.54	23.04	22.41	23.17	0.55%	1.11%	1.66%	21.65	23.93
TiO ₂ , wt. %	1.36	0.020	1.32	1.40	1.30	1.42	1.50%	3.00%	4.51%	1.29	1.43
Zn, ppm	207	12	182	232	170	244	5.96%	11.92%	17.88%	197	218
Thermogravimetry											
LOI ¹⁰⁰⁰ , wt. %	10.18	0.218	9.75	10.62	9.53	10.84	2.14%	4.28%	6.42%	9.67	10.69
Borate / Peroxide Fusion ICP											
Al ₂ O ₃ , wt. %	15.56	0.358	14.85	16.28	14.49	16.64	2.30%	4.60%	6.91%	14.78	16.34
As, ppm	< 30	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Ba, ppm	284	10	264	303	254	313	3.46%	6.92%	10.38%	270	298
Be, ppm	1.43	0.34	0.75	2.11	0.41	2.45	23.87%	47.74%	71.60%	1.36	1.50
CaO, wt. %	0.342	0.048	0.247	0.438	0.199	0.485	13.96%	27.91%	41.87%	0.325	0.359
Ce, ppm	75	4.3	66	83	62	87	5.81%	11.62%	17.43%	71	78
Co, ppm	807	19	768	845	748	865	2.41%	4.81%	7.22%	766	847
Cr ₂ O ₃ , wt. %	0.281	0.008	0.265	0.297	0.257	0.305	2.86%	5.73%	8.59%	0.267	0.295
Cs, ppm	0.86	0.082	0.69	1.02	0.61	1.10	9.54%	19.09%	28.63%	0.81	0.90
Cu, ppm	495	22	451	540	429	562	4.49%	8.98%	13.47%	471	520
Dy, ppm	4.19	0.227	3.74	4.65	3.51	4.88	5.42%	10.83%	16.25%	3.98	4.40
Er, ppm	2.26	0.164	1.93	2.59	1.77	2.75	7.27%	14.53%	21.80%	2.15	2.37
Eu, ppm	1.45	0.097	1.25	1.64	1.16	1.74	6.72%	13.43%	20.15%	1.38	1.52
Fe ₂ O ₃ , wt. %	45.22	1.121	42.98	47.46	41.86	48.58	2.48%	4.96%	7.43%	42.96	47.48
Ga, ppm	22.2	1.85	18.5	25.9	16.6	27.7	8.35%	16.70%	25.05%	21.1	23.3
Gd, ppm	4.83	0.352	4.13	5.54	3.78	5.89	7.29%	14.57%	21.86%	4.59	5.07
Hf, ppm	2.54	0.143	2.25	2.83	2.11	2.97	5.63%	11.25%	16.88%	2.41	2.67
Ho, ppm	0.82	0.051	0.71	0.92	0.66	0.97	6.24%	12.49%	18.73%	0.78	0.86
K ₂ O, wt. %	0.107	0.023	0.062	0.152	0.039	0.174	21.09%	42.18%	63.27%	0.101	0.112
La, ppm	10.1	0.80	8.5	11.7	7.7	12.5	7.98%	15.95%	23.93%	9.6	10.6
Li, ppm	22.2	1.18	19.9	24.6	18.7	25.8	5.29%	10.58%	15.87%	21.1	23.4
Lu, ppm	0.33	0.04	0.26	0.41	0.22	0.45	11.50%	23.00%	34.50%	0.32	0.35
MgO, wt. %	0.773	0.029	0.715	0.831	0.686	0.860	3.75%	7.49%	11.24%	0.735	0.812
MnO, wt. %	1.49	0.041	1.40	1.57	1.36	1.61	2.79%	5.57%	8.36%	1.41	1.56

Note: intervals may appear asymmetric due to rounding.

Table 3 continued.

Constituent	Certified Value	Absolute Standard Deviations					Relative Standard Deviations			5% window	
		1SD	2SD Low	2SD High	3SD Low	3SD High	1RSD	2RSD	3RSD	Low	High
Borate / Peroxide Fusion ICP continued											
Mo, ppm	< 5	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Na ₂ O, wt.%	0.149	0.019	0.111	0.186	0.093	0.205	12.58%	25.16%	37.75%	0.141	0.156
Nb, ppm	4.79	0.293	4.21	5.38	3.92	5.67	6.10%	12.21%	18.31%	4.55	5.03
Nd, ppm	16.6	0.81	15.0	18.2	14.2	19.0	4.87%	9.74%	14.61%	15.8	17.4
Ni, ppm	688	28	631	744	603	772	4.09%	8.18%	12.26%	653	722
P ₂ O ₅ , wt.%	0.150	0.020	0.109	0.191	0.089	0.211	13.61%	27.23%	40.84%	0.143	0.158
Pb, ppm	< 20	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Pr, ppm	3.58	0.180	3.22	3.94	3.04	4.12	5.02%	10.05%	15.07%	3.41	3.76
Rb, ppm	8.15	0.535	7.08	9.22	6.55	9.76	6.56%	13.11%	19.67%	7.74	8.56
Sc, ppm	401	19	364	439	345	458	4.69%	9.37%	14.06%	381	421
SiO ₂ , wt.%	22.52	0.429	21.66	23.37	21.23	23.80	1.91%	3.81%	5.72%	21.39	23.64
Sm, ppm	5.18	0.344	4.49	5.87	4.15	6.21	6.65%	13.29%	19.94%	4.92	5.44
Sn, ppm	2.58	1.22	0.15	5.02	0.00	6.24	47.16%	94.32%	141.48 %	2.45	2.71
Sr, ppm	68	4.8	58	77	53	82	7.14%	14.29%	21.43%	64	71
Ta, ppm	0.38	0.04	0.29	0.47	0.25	0.51	11.74%	23.49%	35.23%	0.36	0.40
Tb, ppm	0.75	0.056	0.64	0.86	0.58	0.92	7.47%	14.95%	22.42%	0.71	0.79
Th, ppm	3.30	0.181	2.93	3.66	2.75	3.84	5.48%	10.97%	16.45%	3.13	3.46
TiO ₂ , wt.%	1.34	0.049	1.24	1.44	1.19	1.49	3.65%	7.29%	10.94%	1.27	1.41
Tm, ppm	0.34	0.04	0.26	0.42	0.23	0.46	11.25%	22.50%	33.75%	0.32	0.36
U, ppm	1.32	0.107	1.10	1.53	1.00	1.64	8.12%	16.23%	24.35%	1.25	1.38
V, ppm	644	33	578	710	545	742	5.10%	10.20%	15.30%	612	676
W, ppm	1.12	0.18	0.75	1.48	0.57	1.66	16.27%	32.53%	48.80%	1.06	1.17
Y, ppm	16.8	1.8	13.1	20.5	11.3	22.3	10.96%	21.92%	32.88%	16.0	17.7
Yb, ppm	2.21	0.124	1.97	2.46	1.84	2.59	5.60%	11.20%	16.80%	2.10	2.33
Zn, ppm	212	13	186	239	173	252	6.19%	12.39%	18.58%	202	223
Zr, ppm	80	5.5	69	91	63	96	6.85%	13.71%	20.56%	76	84
Infrared Combustion											
C, wt.%	0.246	0.016	0.214	0.277	0.199	0.293	6.40%	12.81%	19.21%	0.234	0.258
Gas / Liquid Pycnometry											
SG, Unity	3.21	0.102	3.01	3.42	2.91	3.52	3.17%	6.34%	9.52%	3.05	3.37

Note: intervals may appear asymmetric due to rounding.

PARTICIPATING LABORATORIES

1. ALS, Brisbane, QLD, Australia
2. ALS, Lima, Peru
3. ALS, Vancouver, BC, Canada
4. Argile Analytica, Calgary, Alberta, Canada
5. Bureau Veritas Commodities Canada Ltd, Vancouver, BC, Canada
6. Bureau Veritas Geoanalytical, Adelaide, SA, Australia
7. Bureau Veritas Geoanalytical, Perth, WA, Australia
8. Inspectorate (BV), Lima, Peru

9. Intertek Genalysis, Perth, WA, Australia
10. Intertek Testing Services, Cupang, Muntinlupa, Philippines
11. Intertek Testing Services, Townsville, QLD, Australia
12. Nagrom, Perth, WA, Australia
13. Ni Lab, Pouembout, New Caledonia
14. PT Geoservices Ltd, Cikarang, Jakarta Raya, Indonesia
15. SGS Australia Mineral Services, Perth, WA, Australia
16. SGS Geosol Laboratorios Ltda, Vespasiano, Minas Gerais, Brazil
17. SGS Mineral Services, Townsville, QLD, Australia

PREPARER AND SUPPLIER

Certified reference material OREAS 198 is prepared, certified and supplied by:



ORE Research & Exploration Pty Ltd
37A Hosie Street
Bayswater North VIC 3153
AUSTRALIA

Tel: +613-9729 0333
Fax: +613-9729 8338
Web: www.ore.com.au
Email: info@ore.com.au

It is available in unit sizes of 10g (single-use laminated foil pouches) and 1kg (plastic jars).

INTENDED USE

OREAS 198 is intended for the following uses:

- for the monitoring of laboratory performance in the analysis of analytes reported in Table 1 in geological samples;
- for the verification of analytical methods for analytes reported in Table 1;
- for the calibration of instruments used in the determination of the concentration of analytes reported in Table 1.

STABILITY AND STORAGE INSTRUCTIONS

OREAS 198 is an oxidised reference material and is stable in the laminated foil pouches. Under normal conditions of storage it has a shelf life beyond ten years.

INSTRUCTIONS FOR CORRECT USE

The certified values determined via fusion ICP, C and S by infrared combustion furnace and SG by pycnometry refer to the concentration levels in the packaged state. There is no need for drying prior to weighing and analysis.

In contrast the certified values determined via borate fusion XRF and for LOI at 1000° C are on a dry basis. This requires the removal of hygroscopic moisture by drying in air to

constant mass at 105° C. If the reference material is not dried prior to analysis, the certified values should be corrected to the moisture-bearing basis.

HANDLING INSTRUCTIONS

Fine powders pose a risk to eyes and lungs and therefore standard precautions such as the use of safety glasses and dust masks are advised.

TRACEABILITY

The analytical samples were selected in a manner to represent the entire batch of prepared CRM. This 'representivity' was maintained in each submitted laboratory sample batch and ensures the user that the data is traceable from sample selection through to the analytical results that underlie the consensus values. Each analytical data set has been validated by its assayer through the inclusion of internal reference materials and QC checks during analysis. The laboratories were chosen on the basis of their competence (from past performance in inter-laboratory programs) for a particular analytical method, analyte or analyte suite, and sample matrix. Most of these laboratories have and maintain ISO 17025 accreditation. The certified values presented in this report are calculated from the means of accepted data following robust statistical treatment as detailed in this report.

LEGAL NOTICE

Ore Research & Exploration Pty Ltd has prepared and statistically evaluated the property values of this reference material to the best of its ability. The Purchaser by receipt hereof releases and indemnifies Ore Research & Exploration Pty Ltd from and against all liability and costs arising from the use of this material and information.

QMS ACCREDITED

ORE Pty Ltd is accredited to ISO 9001:2008 by Lloyd's Register Quality Assurance Ltd for its quality management system including development, manufacturing, certification and supply of CRMs.



CERTIFYING OFFICER

A handwritten signature in black ink, appearing to read 'Craig Hamlyn', is positioned above a horizontal line.

Craig Hamlyn (B.Sc. Hons - Geology), Technical Manager - ORE P/L

REFERENCES

ISO Guide 30 (1992), Terms and definitions used in connection with reference materials.

ISO Guide 31 (2000), Reference materials – Contents of certificates and labels.

ISO Guide 3207 (1975), Statistical interpretation of data - Determination of a statistical tolerance interval.

ISO Guide 35 (2006), Certification of reference materials - General and statistical principals.