

CERTIFICATE OF ANALYSIS FOR

HIGH GRADE MANGANESE ORE

CERTIFIED REFERENCE MATERIAL

OREAS 170b

Summary Statistics for OREAS 170b

Constituent (wt.%)	Certified Value	1SD	95% Confidence Interval	
			Low	High
Mn	46.06	0.33	45.82	46.28
MnO	59.46	0.43	59.16	59.75
Fe ₂ O ₃	7.04	0.08	6.99	7.10
SiO ₂	9.49	0.06	9.45	9.53
Al ₂ O ₃	3.90	0.06	3.86	3.94
MgO	0.329	0.018	0.316	0.342
CaO	0.270	0.007	0.265	0.275
TiO ₂	0.189	0.004	0.186	0.191
K ₂ O	1.80	0.04	1.77	1.83
P ₂ O ₅	0.195	0.005	0.192	0.199
Na ₂ O	0.318	0.022	0.301	0.335
LOI	11.95	0.15	11.84	12.06

Note - intervals may appear asymmetric due to rounding

Prepared by:
 Ore Research & Exploration Pty Ltd
 June 2010

SOURCE MATERIAL

OREAS 170b is a high grade supergene manganese ore matrix-matched certified reference material (MMCRM) prepared and certified by Ore Research & Exploration. The material was sourced from the Groote Eylandt Mining Company Pty Ltd (GEMCO) Mn deposit which is hosted within a shallow dipping Lower Cretaceous sedimentary rock unit. Groote Eylandt is in the Gulf of Carpentaria off the coast of Australia's Northern Territory. OREAS 170a is one of two MMCRMs characterised for MnO, Fe₂O₃, SiO₂, Al₂O₃, MgO, CaO, TiO₂, K₂O, P₂O₅, Na₂O and LOI.

COMMUNITION AND HOMOGENISATION PROCEDURES

The material was prepared in the following manner:

- a) *drying at 105° C to constant mass;*
- b) *crushing and multi-stage milling to 100% minus 40 microns;*
- c) *homogenisation;*
- d) *packaging into 1.0 kg units using wide mouth plastic jars.*

ANALYSIS OF OREAS 170b

Ten commercial laboratories participated in the analytical program to characterise MnO, Fe₂O₃, SiO₂, Al₂O₃, MgO, CaO, TiO₂, K₂O, P₂O₅, Na₂O and LOI. Their results together with uncorrected means, medians, one sigma standard deviations, relative standard deviations and percent deviation of lab means from the corrected mean of means (PDM³) are presented in Tables A2 to A12 (Appendix). The parameter PDM³ is a measure of laboratory accuracy while the relative standard deviation is an effective measure of analytical precision where homogeneity of the test material has been confirmed.

The analytical methods employed by each laboratory are explained, together with other abbreviations used, in Table A1 (Appendix).

Each participating laboratory received 5 samples of 20g each. Each set of subsamples submitted to each laboratory was taken at regular intervals during packaging of the standard in order to maximise their representation. All laboratories were instructed to either dry the samples for a minimum of 6 hours (or until constant mass was achieved), then place the samples in a desiccator with fresh desiccant until weighed or alternatively, to equilibrate the samples to the lab atmosphere and correct the results to a dry basis after moisture analysis at 105°C. All labs employed a lithium borate fusion technique with XRF finish to determine the requested oxides. LOI was determined at 1000°C using thermogravimetric methods.

STATISTICAL EVALUATION OF ANALYTICAL DATA FOR OREAS 170b

Certified Value and Confidence Intervals

The certified value is the mean of means of accepted replicate values of accepted participating laboratories computed according to the formulae

$$\bar{x}_i = \frac{1}{n_i} \sum_{j=1}^{n_i} x_{ij}$$

$$\bar{\bar{x}} = \frac{1}{p} \sum_{i=1}^p \bar{x}_i$$

where

x_{ij} is the j th result reported by laboratory i ;
 p is the number of participating laboratories;
 n_i is the number of results reported by laboratory i ;
 \bar{x}_i is the mean for laboratory i ;
 $\bar{\bar{x}}$ is the mean of means.

The confidence intervals were obtained by calculation of the variance of the consensus value (mean of means) and reference to Student's- t distribution with degrees of freedom ($p-1$).

$$\hat{V}(\bar{\bar{x}}) = \frac{1}{p(p-1)} \sum_{i=1}^p (\bar{x}_i - \bar{\bar{x}})^2$$

$$\text{Confidence Interval} = \bar{\bar{x}} \pm t_{1-x/2}(p-1)(\hat{V}(\bar{\bar{x}}))^{1/2}$$

where

$t_{1-x/2}(p-1)$ is the $1-x/2$ fractile of the t -distribution with $(p-1)$ degrees of freedom.

The distribution of the values is assumed to be symmetrical about the mean in the calculation of the confidence interval.

The test for rejection of individual outliers from each laboratory data set was primarily based on z scores (rejected if $|z_i| > 2.5$) computed from the robust estimators of location and scale, T and S , respectively, according to the formulae:

$$S = 1.483 \frac{\text{median}_{j=1, \dots, n} |x_j - \text{median}_{i=1, \dots, n}(x_i)|}{}$$

$$z_i = \frac{x_i - T}{S}$$

where

T is the median value in a data set;
 S is the median of all absolute deviations from the sample median multiplied by 1.483, a correction factor to make the estimator consistent with the usual parameter of a normal distribution.

Table 1. Certified values and 95% confidence intervals for OREAS 170b

Constituent (wt.%)	Certified Value	95% Confidence Interval	
		Low	High
Manganese, Mn	46.06	45.82	46.28
Manganese oxide, MnO	59.46	59.16	59.75
Iron oxide, Fe ₂ O ₃	7.04	6.99	7.10
Silicon dioxide, SiO ₂	9.49	9.45	9.53
Aluminium oxide, Al ₂ O ₃	3.90	3.86	3.94
Magnesium oxide, MgO	0.329	0.316	0.342
Calcium oxide, CaO	0.270	0.265	0.275
Titanium dioxide, TiO ₂	0.189	0.186	0.191
Potassium oxide, K ₂ O	1.80	1.77	1.83
Phosphorus oxide, P ₂ O ₅	0.195	0.192	0.199
Sodium oxide, Na ₂ O	0.318	0.301	0.335
LOI at 1000° C	11.95	11.84	12.06

Note - intervals may appear asymmetric due to rounding

The z-score test is used in combination with a second method of individual outlier detection that determines the percent deviation of the individual value from the median. Outliers in general are selected on the basis of z-scores > 2.5 and with percent deviations > 1.5%. In certain instances statistician's prerogative has been employed in discriminating outliers. Each laboratory data set is tested for outlying status based on z-score discrimination and rejected if $|z_i| > 2.5$. After individual and lab data set outliers have been eliminated a non-iterative 3 standard deviation filter is applied, with those values lying outside this window also relegated to outlying status.

Individual outliers and, more rarely, laboratory means deemed to be outlying are shown left justified and in bold in the tabulated results (see Appendix) and have been omitted in the determination of certified values.

The magnitude of the confidence interval is inversely proportional to the number of participating laboratories and interlaboratory agreement. It is a measure of the reliability of the certified value, i.e. the narrower the confidence interval the greater the certainty in the certified value. A 95% confidence interval indicates a 95% probability that the interval includes the true value of the analyte under consideration.

Statement of Homogeneity

The standard deviation of each laboratory data set includes error due to both the imprecision of the analytical method employed and to possible inhomogeneity of the material analysed. The standard deviation of the pooled individual analyses of all participating laboratories includes error due to the imprecision of each analytical method, to possible inhomogeneity of the material analysed and, in particular, to deficiencies in accuracy of each analytical method.

In determining tolerance intervals that component of error attributable to measurement inaccuracy was eliminated by transformation of the individual results of each data set to a common mean (the uncorrected grand mean) according to the formula

$$x'_{ij} = x_{ij} - \bar{x}_i + \frac{\sum_{i=1}^p \sum_{j=1}^{n_i} x_{ij}}{\sum_{i=1}^p n_i}$$

where

- x_{ij} is the j th raw result reported by laboratory i ;
- x'_{ij} is the j th transformed result reported by laboratory i ;
- n_i is the number of results reported by laboratory i ;
- p is the number of participating laboratories;
- \bar{x}_i is the raw mean for laboratory i .

The homogeneity of each constituent was determined from tables of factors for two-sided tolerance limits for normal distributions (ISO 3207) in which

$$\begin{aligned} \text{Lower limit is } \bar{x} - k'_2(n, p, 1 - \alpha) s_g'' \\ \text{Upper limit is } \bar{x} + k'_2(n, p, 1 - \alpha) s_g'' \end{aligned}$$

where

- n the number of results
- $1 - \alpha$ is the confidence level;
- p is the proportion of results expected within tolerance limits;
- k'_2 is the factor for two-sided tolerance limits (m, α unknown);
- s_g'' is the corrected grand standard deviation.

The meaning of these tolerance limits may be illustrated for manganese oxide, where 99% of the time at least 95% of subsamples will have concentrations lying between 59.27 and 59.64 wt.%. Put more precisely, this means that if the same number of subsamples were taken and analysed in the same manner repeatedly, 99% of the tolerance intervals so constructed would cover at least 95% of the total population, and 1% of the tolerance intervals would cover less than 95% of the total population (ISO Guide 35).

The corrected grand standard deviation, s_g'' , used to compute the tolerance intervals is the weighted means of standard deviations of all data sets for a particular constituent according to the formula

$$s_g'' = \frac{\sum_{i=1}^p (s_i (1 - \frac{s_i}{s_g'}))}{\sum_{i=1}^p (1 - \frac{s_i}{s_g'})}$$

where

$1 - \left(\frac{s_i}{2s'_g} \right)$ is the weighting factor for laboratory i ;

s'_g is the grand standard deviation computed from the transformed (i.e. means - adjusted) results

according to the formula

$$s'_g = \left[\frac{\sum_{i=1}^p \sum_{j=i}^{n_i} (x'_{ij} - \bar{x}'_i)^2}{\sum_{i=1}^p n_i - 1} \right]^{1/2}$$

where \bar{x}'_i is the transformed mean for laboratory i

The weighting factors were applied to compensate for the considerable variation in analytical precision amongst participating laboratories. Hence, weighting factors for each data set have been constructed so as to be inversely proportional to the standard deviation of that data set. It should be noted that estimates of tolerance by this method are considered conservative as a significant proportion of the observed variance, even in those laboratories exhibiting the best analytical precision, can presumably be attributed to measurement error.

Table 2. Certified values and tolerance intervals for OREAS 170b.

Constituent (wt.%)	Certified Value	Tolerance Interval 1- α =0.99, ρ =0.95	
		Low	High
Manganese, Mn	46.06	45.91	46.20
Manganese oxide, MnO	59.46	59.27	59.64
Iron oxide, Fe ₂ O ₃	7.04	7.01	7.07
Silicon dioxide, SiO ₂	9.49	9.45	9.54
Aluminium oxide, Al ₂ O ₃	3.90	3.87	3.93
Magnesium oxide, MgO	0.329	0.326	0.332
Calcium oxide, CaO	0.270	0.270	0.270
Titanium dioxide, TiO ₂	0.189	IND	IND
Potassium oxide, K ₂ O	1.80	1.79	1.81
Phosphorus oxide, P ₂ O ₅	0.195	0.192	0.199
Sodium oxide, Na ₂ O	0.318	0.300	0.336
LOI at 1000° C	11.95	11.90	12.01

Note - intervals may appear asymmetric due to rounding

Performance Gates

Performance gates provide an indication of a level of performance that might reasonably be expected from a laboratory being monitored by this CRM in a QA/QC program. They take into account errors attributable to measurement and CRM variability. For an effective CRM the contribution of the latter should be negligible in comparison to measurement

errors. Sources of measurement error include inter-lab bias, analytical precision (repeatability) and inter-batch bias (reproducibility).

Two methods have been employed to calculate performance gates. The first method uses the same filtered data set used to determine the certified value, i.e. after removal of all individual, lab dataset (batch) and 3SD outliers. These outliers can only be removed after the absolute homogeneity of the CRM has been independently established, i.e. the outliers must be confidently deemed to be analytical rather than arising from inhomogeneity of the CRM. The standard deviation is then calculated for each analyte from the pooled individual analyses generated from the certification program.

Table 3 shows performance gates calculated for two and three standard deviations. As a guide these intervals may be regarded as warning or rejection for multiple 2SD outliers, or rejection for individual 3SD outliers in QC monitoring, although their precise application should be at the discretion of the QC manager concerned. A second method utilises a 5% window calculated directly from the certified value. Standard deviation is also shown in relative percent for one, two and three relative standard deviations (1RSD, 2RSD and 3RSD) to facilitate an appreciation of the magnitude of these numbers and a comparison with the 5% window. Caution should be exercised when concentration levels approach lower limits of detection of the analytical methods employed as performance gates calculated from standard deviations tend to be excessively wide whereas those determined by the 5% method are too narrow.

Table 3. Performance Gates for OREAS 170b

Constituent (wt.%)	Certified Value	Absolute Standard Deviations					Relative Standard Deviations			5% window	
		1SD	2SD Low	2SD High	3SD Low	3SD High	1RSD	2RSD	3RSD	Low	High
Mn	46.06	0.33	45.39	46.72	45.07	47.04	0.72%	1.43%	2.15%	43.75	48.36
MnO	59.46	0.43	58.60	60.31	58.18	60.73	0.72%	1.43%	2.15%	56.48	62.43
Fe ₂ O ₃	7.04	0.08	6.88	7.20	6.80	7.28	1.13%	2.27%	3.40%	6.69	7.39
SiO ₂	9.49	0.06	9.37	9.62	9.31	9.68	0.64%	1.28%	1.92%	9.02	9.97
Al ₂ O ₃	3.90	0.06	3.79	4.02	3.73	4.07	1.46%	2.91%	4.37%	3.71	4.10
MgO	0.329	0.018	0.292	0.366	0.274	0.384	5.56%	11.12%	16.67%	0.313	0.345
CaO	0.270	0.007	0.257	0.283	0.250	0.290	2.45%	4.90%	7.35%	0.257	0.284
TiO ₂	0.189	0.004	0.181	0.197	0.177	0.201	2.11%	4.22%	6.32%	0.179	0.198
K ₂ O	1.80	0.04	1.72	1.87	1.68	1.91	2.09%	4.18%	6.28%	1.71	1.89
P ₂ O ₅	0.195	0.005	0.185	0.206	0.180	0.211	2.67%	5.34%	8.02%	0.185	0.205
Na ₂ O	0.318	0.022	0.273	0.362	0.251	0.385	6.99%	13.99%	20.98%	0.302	0.334
LOI	11.95	0.15	11.64	12.26	11.49	12.41	1.29%	2.59%	3.88%	11.35	12.55

Note - intervals may appear asymmetric due to rounding

PARTICIPATING LABORATORIES

Acme Analytical Laboratories Ltd, Vancouver, BC, Canada

Activation Laboratories, Ancaster, Ontario, Canada

Amdel Laboratories Ltd, Adelaide, SA, Australia

ALS Chemex, Brisbane, QLD, Australia

ALS Chemex, Vancouver, BC, Canada

Genalysis Laboratory Services Pty Ltd, Perth, WA, Australia

OMAC Laboratories Ltd, Loughrea, County Galway, Ireland

SGS Lakefield Research Ltd, Lakefield, ON, Canada

SGS Australia, Perth, WA, Australia

Ultra Trace Pty Ltd, Perth, WA, Australia

PREPARER AND SUPPLIER OF THE REFERENCE MATERIAL

Reference material OREAS 170b has been prepared and certified and is supplied by:

Ore Research & Exploration Pty Ltd
37A Hosie Street
Bayswater North VIC 3153
AUSTRALIA

Telephone (03) 9729 0333
Facsimile (03) 9729 8338
Email info@ore.com.au

International +613-9729 0333
International +613-9729 8338
Web www.ore.com.au

OREAS 170b is available in 10g units packaged in laminated foil pouches or 1kg units in wide mouth plastic jars.

INTENDED USE

OREAS 170b is a reference material intended for the following:

- i) for the monitoring of laboratory performance in the analysis of MnO, Fe₂O₃, SiO₂, Al₂O₃, MgO, CaO, TiO₂, K₂O, P₂O₅, Na₂O and LOI in geological samples;
- ii) for the calibration of instruments used in the determination of the concentration of MnO, Fe₂O₃, SiO₂, Al₂O₃, MgO, CaO, TiO₂, K₂O, P₂O₅, Na₂O and LOI;
- iii) for the verification of analytical methods for MnO, Fe₂O₃, SiO₂, Al₂O₃, MgO, CaO, TiO₂, K₂O, P₂O₅, Na₂O and LOI.

STABILITY AND STORAGE INSTRUCTIONS

OREAS 170b is a reference material made from high grade manganese oxide ore sourced from the Groote Eylandt Mining Company Pty Ltd (GEMCO) Mn deposit. Under normal conditions of storage it has a shelf life beyond five years.

INSTRUCTIONS FOR THE CORRECT USE OF THE REFERENCE MATERIAL

The certified values for OREAS 170b refer to the concentration level of MnO, Fe₂O₃, SiO₂, Al₂O₃, MgO, CaO, TiO₂, K₂O, P₂O₅, Na₂O and LOI after removal of hygroscopic moisture by drying in air to constant mass at 105° C. If the reference material is not dried by the user prior to analysis, the certified values should be corrected to the moisture-bearing basis.

LEGAL NOTICE

Ore Research & Exploration Pty Ltd has prepared and statistically evaluated the property values of this reference material to the best of its ability. The Purchaser by receipt hereof releases and indemnifies Ore Research & Exploration Pty Ltd from and against all liability and costs arising from the use of this material and information.

REFERENCES

ISO Guide 35 (2006), Certification of reference materials - General and statistical principals.
ISO Guide 3207 (1975), Statistical interpretation of data - Determination of a statistical tolerance interval.

QMS ACCREDITED

ORE Pty Ltd is accredited to ISO 9001:2008 by Lloyd's Register Quality Assurance Ltd for its quality management system including development, manufacturing, certification and supply of CRMs.



CERTIFYING OFFICER

A handwritten signature in blue ink, appearing to read 'S. Hamlyn'.

Craig Hamlyn (B.Sc. Hons - Geology), Technical Manager - ORE P/L

APPENDIX

Analytical Data for OREAS 170b

Table A1. Explanation of abbreviations used in Tables A2 – A12.

Abbreviation	Explanation
Std.Dev.	one standard deviation
Rel.Std.Dev.	one relative standard deviation (%)
PDM ³	percent deviation of lab mean from corrected mean of means
NR	not reported
BF	lithium metaborate fusion
LOI	loss on ignition at 1000° C
XRF	x-ray fluorescence

Table A2. Results for MnO in OREAS 170b (abbreviations as in Table A1; values in wt.%).

Replicate No.	Lab A BF*XRF	Lab B BF*XRF	Lab C BF*XRF	Lab D BF*XRF	Lab E BF*XRF	Lab F BF*XRF	Lab G BF*XRF	Lab H BF*XRF	Lab I BF*XRF	Lab J BF*XRF
1	63.25	60.69	59.46	58.70	60.00	59.30	60.00	59.20	59.41	59.60
2	63.15	60.04	59.37	58.67	59.30	59.30	59.68	59.20	59.43	59.70
3	63.29	57.59	59.39	58.56	60.00	59.30	59.61	59.20	59.52	59.60
4	62.88	59.78	59.32	58.77	60.20	59.40	59.60	59.20	59.38	59.70
5	63.17	59.01	59.30	58.65	59.90	59.30	59.72	59.20	59.37	59.60
Mean	63.15	59.42	59.37	58.67	59.88	59.32	59.72	59.20	59.42	59.64
Median	63.17	59.78	59.37	58.67	60.00	59.30	59.68	59.20	59.41	59.60
Std.Dev.	0.16	1.19	0.06	0.08	0.34	0.04	0.16	0.00	0.06	0.05
Rel.Std.Dev.	0.25%	2.00%	0.10%	0.13%	0.57%	0.075%	0.27%	0.00%	0.10%	0.09%
PDM ³	6.21%	-0.06%	-0.15%	-1.32%	0.71%	-0.23%	0.45%	-0.43%	-0.06%	0.31%

Table A3. Results for Fe₂O₃ in OREAS 170b (abbreviations as in Table A1; values in wt.%).

Replicate No.	Lab A BF*XRF	Lab B BF*XRF	Lab C BF*XRF	Lab D BF*XRF	Lab E BF*XRF	Lab F BF*XRF	Lab G BF*XRF	Lab H BF*XRF	Lab I BF*XRF	Lab J BF*XRF
1	7.14	7.16	7.01	6.95	7.10	6.98	6.98	7.18	7.08	7.03
2	7.14	7.06	6.97	6.95	7.05	6.95	6.99	7.18	7.05	7.07
3	7.15	6.76	6.99	6.94	7.10	6.95	6.98	7.17	7.07	7.01
4	7.15	7.04	6.95	6.94	7.09	6.95	7.00	7.17	7.05	7.06
5	7.12	6.93	6.96	6.95	7.06	6.96	6.99	7.18	7.06	6.98
Mean	7.14	6.99	6.98	6.95	7.08	6.96	6.99	7.18	7.06	7.03
Median	7.14	7.04	6.97	6.95	7.09	6.95	6.99	7.18	7.06	7.03
Std.Dev.	0.01	0.15	0.02	0.01	0.02	0.01	0.01	0.01	0.01	0.04
Rel.Std.Dev.	0.17%	2.18%	0.34%	0.08%	0.33%	0.19%	0.15%	0.08%	0.18%	0.52%
PDM ³	1.42%	-0.71%	-0.92%	-1.34%	0.57%	-1.17%	-0.75%	1.93%	0.31%	-0.14%

Table A4. Results for SiO₂ in OREAS 170b (abbreviations as in Table A1; values in wt.%).

Replicate No.	Lab A BF*XRF	Lab B BF*XRF	Lab C BF*XRF	Lab D BF*XRF	Lab E BF*XRF	Lab F BF*XRF	Lab G BF*XRF	Lab H BF*XRF	Lab I BF*XRF	Lab J BF*XRF
1	9.41	9.49	9.57	9.42	9.52	9.49	9.59	9.45	9.52	9.57
2	9.41	9.46	9.54	9.51	9.44	9.51	9.52	9.43	9.49	9.58
3	9.43	9.22	9.57	9.43	9.53	9.50	9.57	9.43	9.49	9.54
4	9.42	9.49	9.59	9.47	9.56	9.48	9.55	9.46	9.50	9.61
5	9.38	9.39	9.57	9.40	9.45	9.55	9.54	9.44	9.48	9.55
Mean	9.41	9.41	9.57	9.45	9.50	9.51	9.55	9.44	9.50	9.57
Median	9.41	9.46	9.57	9.43	9.52	9.50	9.55	9.44	9.49	9.57
Std.Dev.	0.02	0.11	0.02	0.04	0.05	0.03	0.03	0.01	0.02	0.03
Rel.Std.Dev.	0.20%	1.21%	0.18%	0.47%	0.55%	0.28%	0.27%	0.14%	0.16%	0.29%
PDM ³	-0.89%	-0.89%	0.77%	-0.51%	0.06%	0.12%	0.61%	-0.56%	0.01%	0.79%

Table A5. Results for Al₂O₃ in OREAS 170b (abbreviations as in Table A1; values in wt.%).

Replicate No.	Lab A BF*XRF	Lab B BF*XRF	Lab C BF*XRF	Lab D BF*XRF	Lab E BF*XRF	Lab F BF*XRF	Lab G BF*XRF	Lab H BF*XRF	Lab I BF*XRF	Lab J BF*XRF
1	3.95	3.80	3.87	3.88	3.98	3.88	3.99	3.94	3.90	3.92
2	3.94	3.77	3.85	3.89	3.93	3.86	3.94	3.95	3.88	3.92
3	3.98	3.68	3.83	3.87	3.96	3.87	3.95	3.95	3.89	3.91
4	3.96	3.79	3.87	3.84	3.99	3.89	3.97	3.96	3.90	3.90
5	3.96	3.74	3.86	3.91	3.98	3.89	3.94	3.94	3.90	3.89
Mean	3.96	3.76	3.86	3.88	3.97	3.88	3.96	3.95	3.89	3.91
Median	3.96	3.77	3.86	3.88	3.98	3.88	3.95	3.95	3.90	3.91
Std.Dev.	0.01	0.05	0.02	0.03	0.02	0.01	0.02	0.01	0.01	0.01
Rel.Std.Dev.	0.37%	1.29%	0.43%	0.67%	0.60%	0.34%	0.52%	0.21%	0.23%	0.33%
PDM ³	1.44%	-3.74%	-1.13%	-0.61%	1.69%	-0.61%	1.36%	1.18%	-0.20%	0.15%

Table A6. Results for MgO in OREAS 170b (abbreviations as in Table A1; values in wt.%).

Replicate No.	Lab A BF*XRF	Lab B BF*XRF	Lab C BF*XRF	Lab D BF*XRF	Lab E BF*XRF	Lab F BF*XRF	Lab G BF*XRF	Lab H BF*XRF	Lab I BF*XRF	Lab J BF*XRF
1	0.360	0.320	0.296	0.320	0.320	0.330	0.335	0.330	0.340	0.350
2	0.360	0.320	0.300	0.310	0.310	0.330	0.335	0.330	0.340	0.340
3	0.360	0.300	0.296	0.320	0.310	0.320	0.335	0.330	0.350	0.350
4	0.360	0.310	0.296	0.320	0.320	0.330	0.335	0.330	0.340	0.360
5	0.350	0.310	0.300	0.330	0.330	0.330	0.344	0.330	0.340	0.350
Mean	0.358	0.312	0.297	0.320	0.318	0.328	0.337	0.330	0.342	0.350
Median	0.360	0.310	0.296	0.320	0.320	0.330	0.335	0.330	0.340	0.350
Std.Dev.	0.004	0.008	0.002	0.007	0.008	0.004	0.004	0.000	0.004	0.007
Rel.Std.Dev.	1.25%	2.68%	0.75%	2.21%	2.63%	1.36%	1.16%	0.00%	1.31%	2.02%
PDM ³	8.80%	-5.18%	-9.59%	-2.74%	-3.35%	-0.31%	2.29%	0.29%	3.94%	6.37%

Table A7. Results for CaO in OREAS 170b (abbreviations as in Table A1; values in wt.%).

Replicate No.	Lab A BF*XRF	Lab B BF*XRF	Lab C BF*XRF	Lab D BF*XRF	Lab E BF*XRF	Lab F BF*XRF	Lab G BF*XRF	Lab H BF*XRF	Lab I BF*XRF	Lab J BF*XRF
1	0.260	0.280	0.275	0.270	0.270	0.270	0.291	0.270	0.270	0.270
2	0.260	0.280	0.283	0.260	0.270	0.270	0.291	0.270	0.270	0.270
3	0.260	0.270	0.282	0.260	0.270	0.260	0.291	0.270	0.270	0.270
4	0.260	0.280	0.278	0.260	0.270	0.270	0.282	0.270	0.270	0.280
5	0.260	0.270	0.285	0.270	0.270	0.270	0.282	0.270	0.270	0.270
Mean	0.260	0.276	0.281	0.264	0.270	0.268	0.287	0.270	0.270	0.272
Median	0.260	0.280	0.282	0.260	0.270	0.270	0.291	0.270	0.270	0.270
Std.Dev.	0.000	0.005	0.004	0.005	0.000	0.004	0.005	0.000	0.000	0.004
Rel.Std.Dev.	0.00%	1.98%	1.43%	2.07%	0.00%	1.67%	1.69%	0.00%	0.00%	1.64%
PDM ³	-3.73%	2.20%	3.90%	-2.25%	-0.02%	-0.77%	6.36%	-0.02%	-0.02%	0.72%

Table A8. Results for TiO₂ in OREAS 170b (abbreviations as in Table A1; values in wt.%).

Replicate No.	Lab A BF*XRF	Lab B BF*XRF	Lab C BF*XRF	Lab D BF*XRF	Lab E BF*XRF	Lab F BF*XRF	Lab G BF*XRF	Lab H BF*XRF	Lab I BF*XRF	Lab J BF*XRF
1	0.180	0.190	0.195	0.190	0.190	0.200	0.194	0.200	0.190	0.190
2	0.180	0.180	0.191	0.190	0.190	0.190	0.185	0.200	0.190	0.190
3	0.180	0.180	0.194	0.190	0.190	0.190	0.185	0.200	0.190	0.190
4	0.180	0.180	0.190	0.190	0.190	0.190	0.185	0.200	0.190	0.190
5	0.180	0.190	0.192	0.190	0.190	0.190	0.185	0.200	0.190	0.180
Mean	0.180	0.184	0.192	0.190	0.190	0.192	0.187	0.200	0.190	0.188
Median	0.180	0.180	0.192	0.190	0.190	0.190	0.185	0.200	0.190	0.190
Std.Dev.	0.000	0.005	0.002	0.000	0.000	0.004	0.004	0.000	0.000	0.004
Rel.Std.Dev.	0.00%	2.98%	1.07%	0.00%	0.00%	2.33%	2.14%	0.00%	0.00%	2.38%
PDM ³	-4.71%	-2.60%	1.76%	0.58%	0.58%	1.64%	-1.12%	5.87%	0.58%	-0.48%

Table A9. Results for K₂O in OREAS 170b (abbreviations as in Table A1; values in wt.%).

Replicate No.	Lab A BF*XRF	Lab B BF*XRF	Lab C BF*XRF	Lab D BF*XRF	Lab E BF*XRF	Lab F BF*XRF	Lab G BF*XRF	Lab H BF*XRF	Lab I BF*XRF	Lab J BF*XRF
1	1.72	1.79	1.86	1.82	1.78	1.82	1.34	1.81	1.75	1.80
2	1.73	1.79	1.88	1.82	1.76	1.82	1.34	1.81	1.78	1.80
3	1.73	1.74	1.87	1.82	1.78	1.81	1.33	1.81	1.79	1.80
4	1.74	1.79	1.87	1.82	1.78	1.82	1.34	1.81	1.79	1.80
5	1.74	1.78	1.85	1.80	1.77	1.82	1.35	1.81	1.78	1.78
Mean	1.73	1.77	1.87	1.82	1.77	1.82	1.34	1.81	1.78	1.80
Median	1.73	1.79	1.87	1.82	1.78	1.82	1.34	1.81	1.78	1.80
Std.Dev.	0.01	0.02	0.01	0.01	0.01	0.00	0.01	0.00	0.02	0.01
Rel.Std.Dev.	0.48%	1.10%	0.73%	0.49%	0.50%	0.25%	0.46%	0.00%	0.92%	0.50%
PDM ³	-3.57%	-1.23%	3.94%	1.11%	-1.23%	1.22%	-25.4%	0.77%	-1.01%	-0.01%

Table A10. Results for P₂O₅ in OREAS 170b (abbreviations as in Table A1; values in wt.%).

Replicate No.	Lab A BF*XRF	Lab B BF*XRF	Lab C BF*XRF	Lab D BF*XRF	Lab E BF*XRF	Lab F BF*XRF	Lab G BF*XRF	Lab H BF*XRF	Lab I BF*XRF	Lab J BF*XRF
1	0.190	0.194	0.197	0.220	0.200	0.200	0.115	0.198	0.189	0.200
2	0.190	0.194	0.198	0.200	0.190	0.200	0.123	0.198	0.189	0.190
3	0.191	0.187	0.197	0.200	0.190	0.200	0.097	0.199	0.189	0.200
4	0.190	0.191	0.193	0.200	0.190	0.200	0.097	0.199	0.188	0.200
5	0.190	0.190	0.196	0.200	0.190	0.210	0.097	0.198	0.189	0.200
Mean	0.190	0.191	0.196	0.204	0.192	0.202	0.106	0.198	0.189	0.198
Median	0.190	0.191	0.197	0.200	0.190	0.200	0.097	0.198	0.189	0.200
Std.Dev.	0.000	0.003	0.002	0.009	0.004	0.004	0.012	0.001	0.000	0.004
Rel.Std.Dev.	0.24%	1.54%	0.91%	4.38%	2.33%	2.21%	11.8%	0.28%	0.24%	2.26%
PDM ³	-2.56%	-2.05%	0.54%	4.50%	-1.64%	3.48%	-45.8%	1.64%	-3.28%	1.43%

Table A11. Results for Na₂O in OREAS 170b (abbreviations as in Table A1; values in wt.%).

Replicate No.	Lab A BF*XRF	Lab B BF*XRF	Lab C BF*XRF	Lab D BF*XRF	Lab E BF*XRF	Lab F BF*XRF	Lab G BF*XRF	Lab H BF*XRF	Lab I BF*XRF	Lab J BF*XRF
1	0.360	0.330	0.350	0.310	0.310	0.320	0.238	0.340	0.320	0.290
2	0.360	0.330	0.312	0.300	0.300	0.310	0.291	0.340	0.310	0.290
3	0.350	0.320	0.296	0.320	0.300	0.330	0.255	0.340	0.320	0.270
4	0.370	0.340	0.307	0.310	0.310	0.330	0.264	0.330	0.320	0.280
5	0.350	0.380	0.297	0.310	0.300	0.320	0.211	0.330	0.310	0.280
Mean	0.358	0.340	0.312	0.310	0.304	0.322	0.252	0.336	0.316	0.282
Median	0.360	0.330	0.307	0.310	0.300	0.320	0.255	0.340	0.320	0.280
Std.Dev.	0.008	0.023	0.022	0.007	0.005	0.008	0.030	0.005	0.005	0.008
Rel.Std.Dev.	2.34%	6.90%	7.05%	2.28%	1.80%	2.60%	11.75%	1.63%	1.73%	2.97%
PDM ³	12.6%	6.95%	-1.72%	-2.48%	-4.37%	1.29%	-20.7%	5.70%	-0.60%	-11.29%

Table A12. Results for LOI in OREAS 170b (abbreviations as in Table A1; values in wt.%).

Replicate No.	Lab A LOI	Lab B LOI	Lab C LOI	Lab D LOI	Lab E LOI	Lab F LOI	Lab G LOI	Lab H LOI	Lab I LOI	Lab J LOI
1	11.80	12.65	11.90	13.22	11.90	12.20	11.85	11.90	12.06	12.21
2	11.80	11.95	11.91	13.23	11.70	12.10	11.90	11.90	12.05	12.16
3	11.80	11.60	11.93	13.25	11.70	12.10	11.90	11.90	12.05	12.18
4	11.80	12.25	11.86	13.18	11.80	12.10	11.89	11.90	12.03	12.18
5	11.80	11.95	11.89	13.18	11.80	12.10	11.91	11.90	12.02	12.21
Mean	11.80	12.08	11.90	13.21	11.78	12.12	11.89	11.90	12.04	12.19
Median	11.80	11.95	11.90	13.22	11.80	12.10	11.90	11.90	12.05	12.18
Std.Dev.	0.00	0.39	0.03	0.03	0.08	0.04	0.02	0.00	0.02	0.02
Rel.Std.Dev.	0.00%	3.25%	0.24%	0.24%	0.71%	0.37%	0.20%	0.00%	0.14%	0.18%
PDM ³	-1.26%	1.08%	-0.44%	10.5%	-1.43%	1.42%	-0.51%	-0.42%	0.76%	1.99%